

Abstract of the Disclosure:

In a barrier rib material, a filler powder includes from 10% to 90% by mass of a silica powder, from 10% to 90% by mass of an alumina powder, and from 0% to 40% by mass of a titanium oxide powder. The silica powder includes from 25% to 75% by mass of an  $\alpha$ -quartz powder and/or a cristobalite powder, and from 25% to 75% by mass of a quartz glass powder.

TOP SECRET